

GENOMER* 3365

RAHN

Your partner for excellence

Technical Data Sheet Polyester / Polyether Acrylate

Description

Modified polyetherpolyol acrylate. Resin for radically curable inks, coatings and adhesives.

Product Data

Functionality	3
Color Index	≤ 100 APHA
Viscosity, 25°C	100 – 200 mPa*s
Acid Number	≤ 1 mg KOH/g
Density, 20°C	1.11 g/cm ³
Flash Point	> 100°C
Refractive Index, 20°C	1.453
Residual TMPTA	< 0.1%

Properties

The product properties can be described as follows:

- high reactivity hardness and scratch resistance
- high gloss
- good abrasion and solvent resistance
- low yellowing
- low residual TMPTA and solvents

The low base viscosity of the oligomer allows a reduced quantity of monomers in the final formulation.

Application

- flexo inks and varnishes
- screen inks and varnishes
- overprint varnishes
- wood coatings
- printing inks and varnishes for plastic foils (PVC, PE etc.)

The product is used in association with urethane acrylates, polyester or epoxy acrylates and acrylate monomers.

Packaging

- 20 kg net container
- 220 kg net inner-coated steel drum
- 1'000 kg IBC

Storage

Store this product in tightly closed containers in a properly vented storage area under dry conditions away from heat, sparks and open flames. Avoid exposing the material to direct sunlight. Do not store this material under an oxygen-free atmosphere. Shelf life is 6 months from receipt. For additional information, please see Safety Data Sheet.

Precautions

Please refer to Safety Data Sheet.

Labeling

Please refer to Safety Data Sheet.

RAHN AG
Dörflistrasse 120
CH-8050 Zürich
Phone +41 (0)44 315 42 00

RAHN GmbH
Hahnstrasse 70
D-60528 Frankfurt/M
Phone 0800 1 816 015

RAHN USA Corp.
1005 N.-Commons Drive
Aurora IL 60504 USA
Phone +1 630 851 4220

RAHN Trading (Shanghai) Ltd.
Zhuanqiao Town
2350 Duzhuang Road
Shanghai 201108, P.R. of China
Phone +86 21 5442 88 71

EnergyCuring@rahn-group.com

www.rahn-group.com

GENOMER*, GENOCURE*, GENORAD* and GENOPOL* are trademarks of RAHN AG.

We have obtained this information wholly or partially from suppliers and from other sources. As we have no insight into the manufacturing processes and application procedures, the recommendations and suggestions are offered without obligation or guarantee. The customer must determine and test for himself the suitability of the products for its purpose and the substances present or not present in the goods. The details are thus conveyed with every reservation and shall imply no commitment or liability on our part. There will be no legitimate claim for any processing-/consequential damage or responsibility regarding patent infringements. If the material is a development product, we cannot guarantee at this stage a continuous commercial supply and/or a consistent quality, unless specially agreed upon.